CEWELD AlMg 4.5Mn Tig

certilas® THE FILLER METAL SPECIALIST

TYPE

Tig aluminium welding wire with high corrosion resistance

TOEPASSINGEN

Filler metal for Magnesium and Manganese alloyed Aluminium with a maximum Magnesium content of 5%. This alloy shows very good mechanical properties that make it ideal for applications in shipyards, in car and railway industry and constructions of reservoirs and tanks.

EIGENSCHAPPEN

Excellent weldabillity and good mechanical strength combined with good corrosion resistance against seawater are typical for this alloy. The weld deposit is free from porosity due to the special shaving process and cleaning method during production. AlMg4,5Mn is one of the highest grades within the range of aluminum alloys and covers a huge range of alloys. Thicker sections should be preheated (150°C) prior to welding.

CLASSIFICATIE

AWS	A 5.10: ER5183
EN ISO	18273: S Al 5183 (AlMg4,5Mn0,7(A))
F-nr	22

GESCHIKT VOOR

Aluminium alloys: AlMg4,5Mn, AlMg5, AlMg2Mn0,8, AlZnMg1, AlZnMgCu0,5, AlMgSi0,5, AlMgSi1, G-AlMg10, G-AlMg5, G-AlMg3Si, G-AlMg5Si, 3.3545, 3.3547, 3.3535, 3.3555, 3.3206, 3.3210, 3.2315, 3.3211, 3.4335, EN AW 5086, EN AW 5083, EN AW 5019, EN AW 5019, EN AW 6060, EN AW 6005A, EN AW 6082, EN AW 6061, EN AW 7020, EN AC 51300, EN AC 51400,

GOEDKEURINGEN

CE

LASPOSITIES

TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

Si	Mn	Cr	Ti	Fe	Al	Mg
0.07	0.7	0.1	0.09	0.15	Rem.	4.5

MECHANISCHE WAARDEN

Heat Treatment	$R_{P0,2}$ (MPa)	Rm (MPa)	A5 (%)	Impact Energy (J) ISO-V	Hardness
				RT	
As Welded	140	300	25	30	HRc

HERDROGEN

Not required

GAS ACC. EN ISO 14175

I1, I3